

# Rustikal Beermat Board - Quality specification

---

The rustikal beermat board can be produced in a range from **0,8 mm** to **2,3 mm** with sheet widths in a range from **600** to **720 mm** and from **900** to **1060 mm** and sheet lengths from **700** to **1500 mm**.

	Unit	Tolerance	
<b>Thickness</b>	- mm	+ -3%	
<b>Moisture content</b>	8,5 %	+ -1,5%	
<b>Water absorbancy</b>	20 s/ml	+ -10 s	
<b>Surface strength</b>	10 no.	-2 Dennison vax no.	
<b>Brightness, unbleached</b>	66 % ISO	+ -2 % ISO	
<b>Ph level</b>	6,0 %	+ -0,5%	
<b>Roughness, topside backside</b>	4000 ml/min 5500 ml/min	+ -500 + -500	
<b>Sheet length width</b>	- mm - mm	+ -2,0 mm + -1,5 mm	
<b>Density</b>	0,8 mm	310 gsm	+ -3%
	0,9 mm	345 gsm	+ -3%
	1,0 mm	375 gsm	+ -3%
	1,1 mm	415 gsm	+ -3%
	1,2 mm	455 gsm	+ -3%
	1,3 mm	495 gsm	+ -3%
	1,4 mm	530 gsm	+ -3%
	1,5 mm	565 gsm	+ -3%
	1,6 mm	600 gsm	+ -3%
	1,7 mm	635 gsm	+ -3%
	1,8 mm	675 gsm	+ -3%
	1,9 mm	710 gsm	+ -3%
	2,0 mm	750 gsm	+ -3%
	2,1 mm	785 gsm	+ -3%
	2,2 mm	815 gsm	+ -3%
	2,3 mm	845 gsm	+ -3%

16-11-27 GN