

PRODUCT ADVICE

EXTERIOR MASONRY



All Farrow & Ball paints are eco friendly and comply with the latest environmental legislation regarding the VOC (volatile organic compounds) content of paints.

Availability: In 5 litre tins only. In Farrow & Ball colours **excluding:** 30, 42, 43, 50, 51, 56, 74, 93, 95, 96, 212, 217, 220, 222, 223, 248, 253, 254, 255, 256, 268, 269, 278, 279 and 280. Available direct from Farrow & Ball, our Showrooms and selected stockists internationally.

Usage: Durable, breathable, low dirt pickup.
For exterior masonry type surfaces.
Not for use on Lime Render.

Preparation: Ensure all surfaces are sound, clean, dry and free from dirt, grease and other contamination. **Flaking or peeling may occur if painting over weak paint layers.**

New render: All newly rendered surfaces must be permitted to **dry out completely** and are best left to weather for up to 6 months before sealing with any paint system. Farrow & Ball recommend seeking advice from a professional prior to painting.

Any areas that remain powdery or unstable following the drying period, prime with Farrow & Ball Masonry & Plaster Stabilising Primer. Proceed with two coats of Farrow & Ball Exterior Masonry.

Dry new cement rendered surfaces – Farrow & Ball Exterior Masonry is supplied ready for use, but 10% water may be added to assist application on sound bare surfaces.

Old render: Surfaces that are unsound may not successfully accept further paint layers; if in doubt seek professional advice.

Serious structurally damaged surfaces – such as cracking or loose cement must be repaired before paint is applied. Patch prime any repaired or seriously degraded areas with two coats of Farrow & Ball Masonry & Plaster Stabilising Primer. Proceed with two coats of Farrow & Ball Exterior Masonry.

Unsound surfaces – alkaline, powdery or porous surfaces should be primed using Farrow & Ball Masonry & Plaster Stabilising Primer; one or two coats should be applied by brush, working well into the surface. Allow to fully dry. Proceed with two coats of Farrow & Ball Exterior Masonry.

Fungal or algal contaminated surfaces – should be decontaminated with an appropriate treatment or by a solution of diluted bleach and allowed to dry completely. Scrape back unsound surfaces and brush clean before applying Farrow & Ball Masonry & Plaster Stabilising Primer. Proceed with two coats of Farrow & Ball Exterior Masonry.

Lime render: **Exterior masonry is not suitable.** Lime renders are intended to allow water vapour transmission, Farrow & Ball recommends obtaining structural advice from a professional before selecting a coating system.

Considerations: Do not paint in temperatures below 10°C or excessive heat above 30°C.
During summer months avoid painting in direct sunlight.
Do not apply if there is a likelihood of rain.
Best applied early in the day to allow drying before evening condensation.

Disclaimer: The information given in these specification sheets and technical advice – whether verbal, in writing or by way of trials – is for guidance and is given in good faith but without warranty, since skill of application and site conditions are beyond our control. For further information please contact our Customer Services Department. We can accept no liability for the performance of the products arising out of such use, beyond the value of the goods delivered by us. This does not affect your statutory rights.

PAS_UK

PRODUCT ADVICE

EXTERIOR MASONRY



Painting: Please check for colour accuracy prior to use as we will not be liable for decorating costs caused as a result of an incorrect colour being applied. When more than one tin of the same colour is to be used ensure that batch numbers are identical or intermix before use. Stir thoroughly before use.

Once the appropriate surface preparation is completed apply two coats of Farrow & Ball Exterior Masonry by brush or roller, taking care not to apply too thickly in hollows and angled sections.

Clean up: Clean brushes and rollers with warm soapy water.

Cleaning: Washable and wipeable.

Formulation: Based on a styrene acrylic resin, containing a wide spectrum biocide to protect surfaces against algal and fungal attack.

Storage: This product is water based and must be protected from frost and extreme temperatures. Use within 6 months of purchase. We accept no responsibility for the deterioration of contents or packaging after this date.

Disposal: Though water based, please do not dispose of into watercourse. Waste materials must be disposed of in accordance with the Environmental Protection Act 1990 and relevant regulations made there under. For further information contact the Environment Office at your local council.

Health & Safety: Ensure good ventilation during application and drying. Avoid contact with skin and eyes. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. After contact with skin wash immediately with plenty of soap and water or a proprietary skin cleanser. Keep out of reach of children. **Safety Data Sheets are available for professional users on request.**

Environment: **Actual VOC content g/l** 1.7 g/l

VOC content w/w: 0.14 %

Classification: Minimal

2010 max. permitted limit grams per litre 40 g/l

CATEGORY c

Biocidal Products Regulation (EU) 528/2012 This product contains the following biocidal products which are used as in-can preservatives:- 1,2-benzothiazol-3(2H)-one & 2-methylisothiazol-3(2H)-one.
This product also contains the following biocidal products which are used as film preservatives:- Diuron (ISO), Pyrethione zinc & 2-Octyl-2H-isothiazol-3-one.
No nanomaterials are present.
Keep out of the reach of children.
Wear protective gloves (such as Nitrile gloves) and eye protection when using this product.
Avoid contact with skin and eyes.
In case of contact with eyes, rinse immediately with water and seek medical advice.
Do not empty waste paint into drains or rivers.
Contact the local Environmental Department for disposal instructions.
Safety Data Sheet available on request or from www.farrow-ball.com.

Disclaimer: The information given in these specification sheets and technical advice - whether verbal, in writing or by way of trials - is for guidance and is given in good faith but without warranty, since skill of application and site conditions are beyond our control. For further information please contact our Customer Services Department. We can accept no liability for the performance of the products arising out of such use, beyond the value of the goods delivered by us. This does not affect your statutory rights.

PAS_UK

PRODUCT ADVICE

EXTERIOR MASONRY



Coverage	Drying Time	Recoat Time	Sheen Level
Up to 40 m ² per 5 litres.	Touch dry in 1 hour, and drying 3 hours dependant on temperature and humidity.	Re-coat from 5 hours.	2%

Water Vapour Transmission (ASTM D1653-13): 289.9 grams/ m ² /24 hrs measured on two coats. Water Vapour Permeance (ASTM D1653-13): 37.5 grams/ m ² /24 hrs/ mm Hg measured on two coats.	This measures the rate at which water evaporates from the substrate through the paint film, measured over a period of 24 hrs.
---	---

Issue 10 – March 2014

Disclaimer: The information given in these specification sheets and technical advice - whether verbal, in writing or by way of trials - is for guidance and is given in good faith but without warranty, since skill of application and site conditions are beyond our control. For further information please contact our Customer Services Department. We can accept no liability for the performance of the products arising out of such use, beyond the value of the goods delivered by us. This does not affect your statutory rights.

PAS_UK